AD

AD-E403 841

Technical Report ARMET-TR-16027

NANO-RDX ELECTROSTATIC STABILIZATION MECHANISM INVESTIGATION USING DERJAGUIN-LANDAU AND VERWEY-OVERBEEK (DLVO) THEORY

Mouhcine Doukkali Rajen Patel Victor Stepanov

January 2017



U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER

Munitions Engineering Technology Center

Picatinny Arsenal, New Jersey

Approved for public release; distribution is unlimited.

The views, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

The citation in this report of the names of commercial firms or commercially available products or services does not constitute official endorsement by or approval of the U.S. Government.

Destroy by any means possible to prevent disclosure of contents or reconstruction of the document. Do not return to the originator.

UNCLASSIFIED					
REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-01-0188		
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, seast existing data source gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden to Department of Defense, Washington Headquarters Services Directorate for Information Operations and Reports (0704-018 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY)			3. DATES COVERED (From - To)		
January 2017 Final 4. TITLE AND SUBTITLE			5a. CONTRACT NUMBER		
	4. THEE AND CONTINUE				
NANO-RDX ELECTROSTATIC STABILIZATION MECHANISM INVESTIGATION USING DERJAGUIN-LANDAU AND VERWEY-		5b. GRANT NUMBER			
OVERBEEK (DLVO) THEORY		5c. PROGRAM ELEMENT NUMBER			
6. AUTHORS		5d. P	5d. PROJECT NUMBER		
Mouhcine Doukkali, Rajen Patel, Vic	tor Stepanov	5e. T	5e. TASK NUMBER		
		5f. WORK UNIT NUMBER			
7. PERFORMING ORGANIZATION NAME(S	3) AND ADDRESS(ES)		8. PERFORMING ORGANIZATION		
U.S. Army ARDEC, METC			REPORT NUMBER		
Energetics, Warheads & Manufactur (RDAR-MEE-W)	ing Technology Directorate				
Picatinny Arsenal, NJ 07806-5000					
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSOR/MONITOR'S ACRONYM(S)		
U.S. Army ARDEC, ESIC					
Knowledge & Process Management (RDAR-EIK)			11. SPONSOR/MONITOR'S REPORT		
Picatinny Arsenal, NJ 07806-5000			NUMBER(S) Technical Report ARMET-TR-16027		
12. DISTRIBUTION/AVAILABILITY STATEM		<u> </u>			
Approved for public release. Distribu	tion is unlimited.				
13. SUPPLEMENTARY NOTES					
14. ABSTRACT					
This work investigates the electrostatic stabilization mechanism of 1,3,5-trinitroperhydro-1,3,5-triazine (Nano-RDX) suspensions at different electrolyte concentrations using Derjaguin-Landau and Verwey-Overbeek (DLVO) Theory. The van der Waals attractive forces were computed at different Nano-RDX crystal sizes and showed that those forces increased at smaller crystal sizes because of an increase in surface area. The electrical repulsion force was also computed with the thickness of the double layer (Debye length) and showed that the force decay increased with ion concentration. The thickness of the double layer is reduced significantly at greater ionic strengths. Finally, the total interaction energy was calculated as a function of electrolyte concentration and predicts that 100 nm Nano-RDX particles could be stable at low concentration of 0.001 mole/I and unstable at 0.1 mole/I. The DLVO theory could serve as a basic framework to study the electrostatic stability of Nano-RDX suspensions at different electrolyte concentrations.					
13. SUBJEUT TEKNIS					

code) (973) 724-2860 Standard Form 298 (Rev. 8/98) Prescribed by ANSI Std. Z39.18

19a. NAME OF RESPONSIBLE PERSON

19b. TELEPHONE NUMBER (Include area

Derjaguin-Landau and Verwey-Overbeek (DLVO) Theory

Mouhcine Doukkali

18. NUMBER

15

OF PAGES

17. LIMITATION OF

SAR

ABSTRACT

1,3,5-trinitroperhydro-1,3,5-triazine (Nano-RDX)

Debye length

c. THIS PAGE

Electrostatic Stabilization

a. REPORT

U

16. SECURITY CLASSIFICATION OF:

b. ABSTRACT

U

CONTENTS

		Page		
Int	roduction	1		
De	erjaguin-Landau and Verwey-Overbeek Theory	1		
	Van der Waals Attractive Forces Electrical Double Layer Repulsion Forces Total Interaction Force	1 2 5		
Co	onclusions	8		
References				
Di	stribution List	11		
	FIGURES			
1	Van der Waals attractive forces for different Nano-RDX sizes	2		
2	2 The electric double layer illustration (ref. 6) 3			
3	Effect of 1:1 electrolyte concentration on the Nano-RDX electrical double layer forces	4		
4	Effect of 1:1 electrolyte concentration on the Nano-RDX total interaction energy	5		
5	Effect of 1:1 Electrolyte Concentration on the Nano-RDX Interaction Energy curves	6		

INTRODUCTION

Nanocrystals of energetic materials exhibit enhanced performance, insensitivity, and mechanical strength in comparison to conventional coarse energetics. While processing methods are currently capable of pound scale production, one of the key remaining challenges for nanocrystals is agglomeration during processing. The interaction forces between nanoparticles in all suspensions play an important role in determining the stability of the nanocrystals. In the 1940s, Derjaguin-Landau and Verwey-Overbeek (DLVO) developed a theory to account for those interaction forces that could provide a basic framework to study the stability of the 1,3,5-trinitroperhydro-1,3,5-triazine (Nano-RDX).

DERJAGUIN-LANDAU AND VERWEY-OVERBEEK THEORY

The DLVO theory (refs. 1 and 2) is built on the assumption that the stability of colloids is determined by two main interaction forces, the van der Waals attractive forces V_a and the electric double layers repulsive forces V_r . The DVLO theory suggests that the stability of a colloidal system is determined by the sum of these van der Waals attractive (V_a) and electrical double layer repulsive (V_r) forces that exist between particles as they approach each other:

$$V_{total} = V_a + V_r \tag{1}$$

This theory proposes that the stability of a colloidal system is determined by competition between the van der Waals attraction and electrostatic repulsion forces.

Van der Waals Attractive Forces

There are three different possible origins for van der Waals forces: (1) permanent dipole-permanent dipole (Keesom) forces, (2) the permanent dipole-induced dipole (Debije) interactions, and (3) transitory dipole-transitory dipole (London) forces. The first two are very short range interactions, but the London forces are longer range attractions. Since only London forces contribute to the long-range attraction between colloidal particles, the magnitude and range of the van der Waals-London attraction are decisive in determining strategies for stabilizing colloid particles.

The van der Waals energy for two interacting spheres of radius r separated by distance h was computed by Hamaker (ref. 3):

$$V_a = -\frac{A_{12}r}{12h} (2)$$

where A_{12} is the Hamaker constant. The Hamaker constant could be easily computed from the Tabor-Winterton (refs. 4 and 5) approximation for RDX in water as a case study:

$$A_{12} = \frac{3}{4} k_b T \left(\frac{\varepsilon_1 - \varepsilon_2}{\varepsilon_1 + \varepsilon_2} \right)^2 + \frac{3h\omega_e}{16\sqrt{2}} \frac{(n_1^2 - n_2^2)^2}{(n_1^2 + n_2^2)^{3/2}} = 1.78 X 10^{-20} J$$
 (3)

where n_1 and n_2 are the index of refraction of RDX and water. ω_e is the electronic relaxation frequency which is assumed to be constant for all materials, ϵ_1 and ϵ_2 are the dielectric constants of RDX and water at 5 MHZ.

Figure 1 shows the calculated van der Waals force from equation 1 for different Nano-RDX crystal sizes. We can easily see from figure 1 that the van der Waals force increases for small crystal size due to their larger surface area.




Figure 1
Van der Waals attractive forces for different Nano-RDX sizes

Electrical Double Layer Repulsion Forces

Nanocrystals in water or in any liquid of high dielectric constant usually develop surface charges, due either to dissociation of chemical groups on the surface or by physical adsorption of ions from the electrolyte. To maintain electro-neutrality, an equal number of counter ions with the opposite charge will surround the colloidal particles and give rise to overall charge-neutral double layers. A diagram of a particle in solution with an electric double layer can be seen in figure 2.




Figure 2
The electric double layer illustration (ref. 6)

The liquid layer surrounding the particle exists as two parts: an inner region (Stern layer) where the ions are strongly bound and an outer (diffuse Gouy-Chapman Layer) region where they are less firmly associated. Generally, the larger the radius of the electrical double layer is, the more dispersed the crystals. Thus, if the electric potential associated with the double layer is sufficiently high, the electrostatic repulsion between the particles prevents agglomeration. The electrostatic double-layer interactions can be estimated by means of the well-known Hogg-Healy-Fuerstenau formula (ref. 7), given by:

$$V_r = 2\pi e_0 \,\varepsilon \, r\varphi^2 \ln\left(1 + e^{-\frac{h}{\kappa^{-1}}}\right) \tag{4}$$

Where e_0 is the permittivity of free space, ε is the solution dielectric, φ is the nanoparticle potential surface, h is the distance between two spherical nanoparticles, and κ is the reciprocal of the Debye length. Debye length which represents the thickness of the double layer is given by (ref. 8):

$$\kappa^{-1} = \sqrt{\frac{e_0 \varepsilon k_e T}{2 N_a e^2 I}} \tag{5}$$

Where e is the electron charge and I is the ionic strength of the electrolyte solution.

In an electrostatic-regulated system, the degree of dispersion is controlled by adjusting the ionic strength. Salts can be added to the solution, and their ions can be adsorbed onto the particle surface to change the particle's net surface charge by modifying the electric double layer (ref. 9).

Figure 3 shows the calculated electrical repulsion force from equation 4 for 100nm Nano-RDX. As we can see from the figure, the decay increases with ion concentration, because there are more counter ions available to cancel the surface potential.




Figure 3
Effect of 1:1 electrolyte concentration on the Nano-RDX electrical double layer forces

The thickness of the double layer (Debye length) is reduced significantly with increasing ionic strength. At low ionic strenghs (0.001 mol/L), the thickness of the double layer is about 9.71 nm, which is the same order of magnitude as the van der Waals attraction (fig. 1). At ionic strenghs (0.1 mol/L), the thickness is less than 1 nm. In that case, the range of double layer electrostatic repulsion is usually insufficent to counterbalance the van der Waals attraction. This accounts for the fact that most charge stabilized dispersions coagulate when increasing the ionic strength of the dispersion. However, there is a trade off when adding ions to a solution. If more ions are added to a solution, then the ionic strength of the solution increases to a larger value. As the ionic strength increases, the thickness of the electric double layer shrinks, which increases the likelihood that particles will collide and agglomerate.

Total Interaction Force

The stability of a Nano-RDX system is determined by the sum of van der Waals attractive (V_a) and electrical double layer repulsive (V_r) forces. The total calculated interaction energy from equation 1 is shown as a function of electrolyte concentration in figure 4. Each individual interaction energy curve for each concentration is shown in figure 5, showing both the electrical double layer repulsive and van der Waals attractive forces. It is quite clear from figures 4 and 5 that depending on the electrolyte concentration, different phase behaviors may occur: (a) At concentration 0.001 m/L, surfaces repel strongly, small Nano-RDX (200 nm) particles remain stable with a maximum total energy of $40 \ k_b T$. If that barrier is greater than $20 \ k_b T$, it is generally assumed that there is not enough Brownian motion to force the Nano-RDX to agglomerate due to van der Waals attraction forces. The thickness of the electrical double layer is around $10 \ \text{nm}$. (b) At concentration $0.01 \ \text{m/L}$, the maximum total energy is around $22 \ k_b T$ and it get below the barrier of $20 \ k_b T$ at 3 nm distance which correspondent to the thickness of the electrical double layer. This concentration could be considered as the border line between the stability and instability of Nano-RDX. (c) At concentration $0.1 \ \text{m/L}$, the van der Waals attraction force is dominant. This explain why most charged nanoparticles agglomerate when increasing the electrolyte concentration of the dispersion.






Figure 4
Effect of 1:1 electrolyte concentration on the Nano-RDX total interaction energy




(a) 0.001 mole/L



(b) 0.01 mole/L

Figure 5
Effect of 1:1 Electrolyte Concentration on the Nano-RDX Interaction Energy curves



(c) 0.1 mole/L

Figure 5 (continued)

CONCLUSIONS

Derjaguin-Landau and Verwey-Overbeek (DLVO) theory predicts that 100nm Nano-RDX particles could be stable at concentrations as low as 0.001 mole/L and unstable at 0.1 mole/L. The surface potential charge of Nano-RDX is assumed to be -30 mv, but this value must be confirmed experimentally. DLVO theory could serve as a basic framework to study the electrostatic stability of Nano-RDX at different electrolyte concentration. This stabilization could be easily regulated by adjusting the salt concentration in the Nano-RDX solution, making it cost effective and easily implemented.

REFERENCES

- Derjaguin, B. V. and Landau, L. D., "Theory of the stability of strong charged lyophobic sols and the adhesion od strongly charged particles in solutions of electrolytes," *Acta. Physicochim* URSS, 14, 633, 1941.
- 2. Verwey, E. J. and Overbeek, J. T., "Theory of the stability of lyophobic colloids," Elsevier Publishing Company, Inc., Amsterdam, 1948.
- 3. Hamaker, H.C., "The London-van der Waals attraction between spherical particles," Physica 1937, 4, 1058-1072.
- 4. Gregory, J., "Calculation of Hamaker Constants, Advanced Colloid Interface," Vol. 2, pp. 396-417, 1969.
- Jonathan, Processing energetics materials with supercritical fluid precipitation techniques. PhD thesis, 2012.
- 6. Adair, J. H., Materials Science 597B Class Notes, *Powder Dispersion*, the Pennsylvania State University, spring 2010.
- 7. Hogg, R.I.; Healey, T.W.; Fuerstenau, D.W. Mutual coagulation of colloidal dispersions. Trans. Faraday Soc. 1966, 62, 1638-1651.
- 8. Derjaguin, B.V. Friction and adhesion IV. The theory of adhesion of small particles. *Kolloid Z* 1934, 69, 155-164.
- 9. Lyklema, J., Fundamentals of Interface and Colloid Science: Volume IV Particulate Colloids, 2005, Elsevier Academic Press, Amsterdam, pp 3.1-3.186.

DISTRIBUTION LIST

U.S. Army ARDEC ATTN: RDAR-EIK

RDAR-MEE-W, M. Doukkali

R. Patel

V. Stepanov

Picatinny Arsenal, NJ 07806-5000

Defense Technical Information Center (DTIC) ATTN: Accessions Division 8725 John J. Kingman Road, Ste 0944 Fort Belvoir, VA 22060-6218

GIDEP Operations Center

Corona, CA 91718-8000

gidep@gidep.org

P.O. Box 8000

REVIEW AND APPROVAL OF ARDEC REPORTS

THIS IS A:					
TECHNICAL REPORT	SPECIAL REPORT				
MEMORANDUM REPORT	ARMAMENT GRADUATE SCHOOL REPORT				
FUNDING SOURCE					
Title Project					
M. Doukkali, R.Patel, V.Stepanov TR-16027/ Jan-2016					
Author/Project Engineer	ARINET -TR- 1602 T Report number/Date received (to be completed by LCSD)				
2860 3022	RDAR-MEE-W				
Extension Building	Author's Office Symbol				
PART 1. Must be signed before the report of	can be edited.				
 The draft copy of this report has be for editing. 	been reviewed for technical accuracy and is approved				
b. Use Distribution Statement A_X_, B, C, D, E, or F for the reason					
checked on the continuation of this					
 If Statement A is selected, the report will be released to the National Technical Information Service (NTIS) for sale to the general public. Only unclassified reports whose distribution is not limited or controlled in any way are released to NTIS. 					
Technical Information Cente	 If Statement B, C, D, E, or F is selected, the report will be released to the Defense Technical Information Center (DTIC) which will limit distribution according to the conditions indicated in the statement. 				
 The distribution list for this report has been reviewed for accuracy and completeness. 					
	Steven Nicolich				
	Division Chief (Date)				
PART 2. To be signed either when dreft recent	t is submitted or after review of reproduction copy.				
This report is approved for publication	Steven Nicolich				
Division Chief (Date)					
Andrew Pskowski					
	RDAR-CIS (Date)				
LCSD 49 (1 Sept 16) supersedes SMCAR Form 49, 20 Dec 06					